Fiber Mulch

Net Weight 50 Pounds



Paper Fiber Mulch

1. Paper fiber mulch is derived from 100% quality recycled newspaper, kraft paper, cardboard, paper mill sludge, and other grades of pre and post consumer waste paper.
2. Flocculating tackifier increases yield – so every bag goes farther providing greater loft within the matrix and outstanding erosion control performance.
3. It is free of extraneous foreign material such as metals, plastic and glass that will adversely affect the service quality of the hydraulic applied fiber mulch.
4. It is hydraulically applied within a water slurry to the soil surface from a hose or tower nozzle.
5. It provides a protective cover for germination and growth as well as soil stabilization at the speed germination zone.

Handling and Storage

Protect damage from weather, excessive temperatures and construction operations. Keeping dry is recommended.

Suggested Application Rates

Condition	Rate
Modest to 4 to 1 Slope	2200 lbs./acre
3 to 1 Slope	2650 lbs./acre
3:1 to 2:1 Slope	3250 lbs./acre

Test Result

Water-Holding Capacity: 930% min.

Moisture Content: 14.80%

Organic Matter: 99.6

Ash Content: 0.76

pH Range: 7.2

Boron: 22.8ppm

TOYO GREENLAND INC.

2437 Shattuck Avenue, Suite 18,
Berkeley, California 94704, USA
Tel :(510) 841-3037
Fax :(510) 841-7113
E-mail :enquiry@toyogreen.com
Web :www.toyogreen.com

Fiber Mulch

Paper Fiber Mulch

1. Paper fiber mulch is derived from 100% quality recycled newspaper, kraft paper, cardboard, paper mill sludge, and other grades of pre and post consumer waste paper.
2. Flocculating tackifier increases yield-so every bag goes further providing greater loft within the matrix and outstanding erosion control performance.
3. It is free of extraneous foreign material such as metals, plastic, and glass that will adversely affect the service quality of the hydraulic applied fiber mulch.
4. It is hydraulically applied within a water slurry to the soil surface from a hose or tower nozzle.
5. It provides a protective cover for germination and growth as well as soil stabilization at the speed germination zone.





Handling and Storage

Protect damage from weather, excessive temperatures and construction operations. Keeping dry is recommended.

Test Data

Water-Holding Capacity : 930% min.
Moisture Content : 14.80%
Organic Content : 99.6%
Ash Content : 0.76
pH Range : 7.2

Suggested Application Rates

Condition	Rate
Modest to 4 :1 Slope	200 lbs./acre
3:1 Slope	2650 lbs./acre
3:1 to 2:1 Slope	3250 lbs./acre

TOYO GREENLAND CO., LTD.
東陽綠化有限公司
No.39, Middle Section, Wa Shan Tsuen, Sheung Shui, N.T., Hong Kong
Tel 電話 : (852) 2639 9312 傳真 : (852) 2377 2150
Web-site 網站 : www.toyogreen.com E-mail 電郵 : danielho@toyogreen.com